Electrochemical Removal of NO_x-Gasses by Use of LSM and LSF Cathodes Impregnated with NO_x-Storage Compounds

Traulsen, Marie Lund; Kammer Hansen, Kent

Published in:
Meeting Abstracts - Electrochemical Society

Publication date:
2010

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Traulsen, M. L., & Kammer Hansen, K. (2010). Electrochemical Removal of NO_x-Gasses by Use of LSM and LSF Cathodes Impregnated with NO_x-Storage Compounds. In *Meeting Abstracts - Electrochemical Society* (pp. Abstract 720). The Electrochemical Society.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Electrochemical removal of NO_x-gasses
by use of LSM and LSF cathodes
impregnated with NO_x-storage compounds

M. L. Traulsen & K. K. Hansen
Fuel Cells and Solid State Chemistry Division
Risø National Laboratory for Sustainable Energy
Technical University of Denmark
4000 Roskilde, Denmark

Electrochemical reduction of NO_x is a potential method for cleaning exhaust gasses from for example diesel engines. In other studies numerous cathode materials have been investigated for reduction of NO_x, for a review see (1). One of the promising cathode materials for NO_x-removal is lanthanum manganite doped with 15 % strontium (LSM15) (2). However, in order to make electrochemical reduction of NO_x an efficient process there is a need to improve the selectivity of the LSM15 cathodes towards NO_x-reduction.

This present work studies the possibility of improving the selectivity of LSM15 and LSF15 cathodes towards NO_x reduction by impregnating the cathodes with alkali and alkali earth nitrates. It is known from the conventional NSR (NO_x Storage and Reduction) catalysis these alkali and alkali earth nitrates can act as NO_x-storage materials by cycling between the nitrate and the corresponding oxide-compound.

In this study cathodes impregnated with different alkali- and alkali earth nitrates are investigated both in a 3-electrode set-up and as electrodes in porous 11-layer cell stacks, in both cases with CGO as electrolyte. The measurements are made in atmospheres containing 1000 ppm NO, 10 % O₂ and 1000 ppm NO+10 % O₂ in the temperature range 300-500 °C. The effect of combining electrochemical reduction of NO_x with a NO_x storage compound is studied with cyclic voltammetry (CV) and electrochemical impedance spectroscopy (EIS). Also, the ability of the electrodes to convert NO_x is monitored by prolonged polarization of the electrodes coupled with mass spectroscopy on the outlet gas. Figure 1 and Figure 2 depicts the NO concentration measured by a mass spectrometer during polarization of an un-impregnated and a sample impregnated with KNO₃, respectively. As seen when comparing Figure 1 and Figure 2, there is a clear effect on the NO_x conversion of impregnating the cathodes with KNO₃. Finally, the cells' microstructure is characterized before and after testing using scanning electron microscopy.

REFERENCES

1. K. K. Hansen, *Appl. Catal. B*, **58**, 33 (2005).
2. K. K. Hansen, E. M. Skou and H. Christensen, *J. Electrochem. Soc.*, **147** (5), 2007 (2000).

Figure 1: NO concentration in ppm in gas stream after passage through a porous 11-layer cell stack with LSM15-CGO10 electrodes and CGO10 electrolyte. The temperature of the cell stack was 300 °C, the inlet gas 1000 ppm NO in Ar, and no effect on the NO concentration was observed when the stack was polarized at -3V (polarization start and end marked by the green and the red line respectively).

Figure 2: Same set-up as in Figure 1, apart from the porous cell stack tested was impregnated with KNO₃. During polarization at -3V approximately 50% conversion was observed, when the conversion was highest.