



Revealing the extra-high ductility and toughness of micro+duplex medium+Mn steel in a large temperature range from 200 to -196

Cao, Wenquan ; Hu, Jun; Dong, Han ; Zhang, Xiaodan

Published in:

Proceedings of the Risø International Symposium on Materials Science

Publication date:

2014

[Link back to DTU Orbit](#)

Citation (APA):

Cao, W., Hu, J., Dong, H., & Zhang, X. (2014). Revealing the extra-high ductility and toughness of micro+duplex medium+Mn steel in a large temperature range from 200 to -196 . *Proceedings of the Risø International Symposium on Materials Science*, 35, 213-220.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

REVEALING THE EXTRA-HIGH DUCTILITY AND
TOUGHNESS OF MICRO-DUPLEX MEDIUM-MN STEEL IN A
LARGE TEMPERATURE RANGE FROM 200°C TO -196°C

Wenquan Cao*, Jun Hu***, Han Dong* and Xiaodan Zhang***

* Central Iron & Steel Research Institute (CISRI), Beijing 100081,
China

** School of Materials Science and Engineering, Huazhong University
of Science and Technology, Wuhan 430074, China

*** Danish-Chinese Center for Nanometals, Materials Science and
Advanced Characterization, Department for Wind Energy, Technical
University of Denmark, DK-4000 Roskilde, Denmark

ABSTRACT

A medium-Mn steel (0.2C5Mn) was processed by intercritical annealing at different temperature (625°C and 650°C) after forging and hot rolling. The microstructures were characterized by transmission electron microscopy and the mechanical properties were measured by tensile tests and impact tests at different temperatures. It was found that an ultrafine grained micro-duplex structure existed with austenite and ferrite laths formed by means of an austenite reverse transformation during intercritical annealing (shortly called ART-annealing). Ultrahigh ductility (total elongation larger than 30%) could be obtained in the temperature range from 200°C to -196°C. And significantly delayed transition from ductile to brittle and no less than 200J impact toughness at -40°C could be obtained in the ART-annealed medium-Mn steel. Based on the analysis of microstructure and mechanical properties, the enhanced ductility in the full temperature range could be ascribed to the phase transformation effect of austenite (TRIP effects), while the delayed ductile to brittle transition could be attributed to the enhanced austenite stability.

1. INTRODUCTION

Steels are required to provide high strength, high ductility, and high toughness under different temperatures covering a large range, for example, vehicles, vessels, and pipelines work from a low temperature below -100°C to a high temperature close to 100°C. Thus a thorough understanding on the knowledge of mechanical properties at varied temperature is essential for the design and application of steels. Recently, new pipeline steels have been proposed to resist

process, thus the carbon content in the austenite ~0.82% in steel 625 and 0.55 % in steel 650 could be estimated under the assumption that the carbon is about 0.02% in ferrite. And the Mn content in the austenite is calculated to be ~10.0% in steel 625 and 9.0% in steel 650 by the commercial software of Thermo-CALC, which is in a good agreement with the experimental values (Lis and Lis 2008). Based on these data, the start temperature of the martensite transformation (M_s) is ~-94°C for the steel625 and ~25°C for the steel650 according to the equation of $M_s=499-316.7C\%-33.3Mn\%$. The strain induced martensite transformation start temperature is about 25°C for the 625steel and 100°C for the 650steel.

It can be seen from Fig.4 that the start decreasing temperature of the impact toughness is about ~-25°C for the 625steel and ~100°C for the 650steel. The ductile to brittle transformation temperature (50% impact toughness decreasing) is about ~-90°C for the 625 steel and ~30°C for the 650 steel. It is very interesting that the start falling temperature of the impact toughness is nearly the same as that of the starting temperature of the strain induced phase transformation (M_σ), whereas the ductile to brittle transformation temperature (half toughness temperature) is nearly the same of that the starting transformation temperature of martensite (M_s) for both steels. This means that the deformation behaviour of the ductile to brittle transformation measured by impact toughness is mainly controlled by the stability of the austenite in the medium-Mn steel treated by intercritical annealing, which provides us the way to design a high ductility and high toughness steel by the control of the stability of the austenite in the multiphase structured steel.

Table 2. Phase transformation and ductile to brittle transformation temperatures

Steel	Half toughness temperature	M_s	Toughness start decreasing	M_σ
steel625	-90°C	-94°C	25°C	25°C
steel650	30°C	25°C	100°C	100°C

5. CONCLUSIONS

In this study, a medium-Mn steel (0.2C5Mn) was processed by relatively long-time ART-annealing at different temperatures. The conclusions can be made as follows.

1. Long time annealing in the intercritical region results in a large volume fraction of austenite with an ultrafine grain size in the medium-Mn steel.
2. The medium-Mn steel after long time intercritical annealing has a good combination of strength, ductility and impact toughness in a large temperature range from -196°C to 100°C.
3. The extra high ductility of the studied steel could be ascribed to the TRIP effects of the large content austenite with an ultrafine grain size.
4. The deformation transition of ductile to brittle can be related to the stability of the retained austenite based on the experiments and calculation.

ACKNOWLEDGEMENTS

W.C., J.H. and H.D. gratefully acknowledge the support from the National Natural Science Foundation of China (NSFC) No. 51371057 and the National Basic Research Program of China (973 Program) No.2010CB630803. X.Z. gratefully acknowledges the support from the Danish

National Research Foundation (Grant No. D NRF86-5) and the National Natural Science Foundation of China (Grant No. 51261130091) to the Danish – Chinese Center for Nanometals.

REFERENCES

- Cao W.Q., Wang C., Wang C.Y., Shi J., Wang M.Q., Dong H., Weng Y.Q., (2012). Microstructures and mechanical properties of the third generation automobile steels fabricated by ART-annealing. *Science China Technological Sciences*, 55, 1814-22.
- Chen Y. and Mao Y., (2009). Review on the high strength pipeline steel of Japan. *Welded Pipe*, 32, 64.
- Fultz B., Kim J.I., Kim Y.H., Kim H.J., Fior G.O., Morris J.W., (1985). The Stability of Precipitated and the Toughness of 9Ni Steel. *Metall. Trans. A*, 16, 2237-49.
- Grassel O., Frommeyer G., (1998). Effect of martensitic phase transformation and deformation twinning on mechanical properties of Fe-Mn-Si-Al steels. *Materials Science and Technology*, 14, 1213-6.
- Hwang S K, Jin S , Morris J W., (1975). Study of Retained Austenite in a Fine Grained Fe212 Ni20125 Ti Alloy. *Metall. Trans*, 6, 2015
- Lis J. and Lis A., (2008). Kinetics of the austenite formation during intercritical annealing. *J. Achievements in Materials and Manufacturing Engineering*, 26, 195-8.
- Shi J., Sun X., Wang M., Hui W., Dong H., Cao W., (2010). Enhanced work-hardening behavior and mechanical properties in ultrafine-grained steels with large-fractioned metastable austenite, *Scripta Materialia*, 63, 815-8.
- Shi J., Xu H.F., Zhao J., Cao W.Q., Wang C., Wang C.Y., Li J., Dong, H., (2013). Effect of austenization temperature on the microstructure evolution of the medium manganese steel (0.2C-5Mn) during ART-annealing. *Acta Metallurgica Sinica-English Letters*, 25, 111-23.
- Strife J.R., Passoja D.E., (1980). The effect of heat treatment on microstructure and cryogenic fracture properties in 5Ni and 9Ni Steel. *Metallurgical and Materials Transactions A*, 11,1341-50.
- Suzuki N., Toyoda M., (2002). Seismic Loading on Buried Pipelines and Deformability of High Strength Linepipes. In: Toyoda M, Denys R. eds. *Proceedings of International Conference on the Application and Evaluation of High Grade Linepipes in Hostile Environments*, Yokohama , Japan Scientific Surveys Ltd, 601-628
- Tamura I. and Wayman C.M., (1992). Martensitic Transformations and Mechanical Effects. In GB Olson and WS Owen, eds., *Martensite*, ASM International, Ch. 12.
- Wang C., Cao W.Q., Shi J., Huang C., Dong H., 2013. Deformation microstructures and strengthening mechanisms of an ultrafine grained duplex medium-Mn steel. *Materials Science and Engineering A*, 562, 89-95.