



Enhancing SOEC system lifetime by controlling inlet gas composition

Friis Pedersen, Claus Flemming; Bech, Lone; Duhn, Jakob Dragsbæk; Jakobsson, Niklas Bengt

Publication date:
2015

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Friis Pedersen, C. F., Bech, L., Duhn, J. D., & Jakobsson, N. B. (2015). IPC No. H01M 8/ 12 A N. Enhancing SOEC system lifetime by controlling inlet gas composition. (Patent No. EP2933357).

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

(19)



(11)

EP 2 933 357 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

21.10.2015 Bulletin 2015/43

(51) Int Cl.:

C25B 15/00 (2006.01)

H01M 8/04 (2006.01)

H01M 8/12 (2006.01)

(21) Application number: **14164564.8**

(22) Date of filing: **14.04.2014**

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

Designated Extension States:

BA ME

• **BECH, Lone**

4100 Ringsted (DK)

• **DRAGSBÆK DUHN, Jakob**

2800 Kgs. Lyngby (DK)

• **JAKOBSSON, Niklas Bengt**

26023 Kågeröd (SE)

(71) Applicant: **Haldor Topsøe A/S**

2800 Kgs. Lyngby (DK)

(74) Representative: **Haldor Topsøe A/S**

Nymøllevej 55

2800 Kgs. Lyngby (DK)

(72) Inventors:

• **FRIIS PEDERSEN, Claus**

DK-2720 Vanløse (DK)

(54) **Enhancing SOEC system lifetime by controlling inlet gas composition**

(57) In a method for enhancing the lifetime of a solid oxide electrolysis cell system by counteracting nitridation of the threads of the in-line electrical heaters of the system, the start-up, shut-down and trip operations are done in a humidified nitrogen atmosphere on the fuel side to

achieve a dew point between -70°C and 23°C, and in air or in carbon dioxide on the oxygen side, securing that sufficiently oxidizing conditions are always present across the whole surface of the cells on the oxygen side in the stack.

EP 2 933 357 A1

Description

[0001] The present invention relates to a method for enhancing the lifetime of a solid oxide electrolysis cell (SOEC) system by controlling the composition of the inlet gas being fed to the system.

[0002] An electrolysis cell uses electricity to split e.g. water molecules (H_2O) into hydrogen (H_2) and oxygen (O_2). In this way, electrical energy is transformed into chemically bound energy in the hydrogen molecules. This is the reverse of the process that occurs in a fuel cell.

[0003] A solid oxide electrolysis cell is basically the corresponding fuel cell (solid oxide fuel cell or SOFC) run in reverse. Such a cell operates at relatively high temperatures (700-1000°C), which makes the efficiency very high. The two electrolysis products, hydrogen and oxygen, are formed on each side of the cell. SOECs may be used for the production of hydrogen from surplus electricity generated by e.g. wind turbines. The hydrogen can be stored and, by means of a fuel cell, reconverted into electricity again when the demand arises. This allows the storage of electricity when production exceeds demand.

[0004] An SOEC can also electrolyze carbon dioxide (CO_2) to carbon monoxide (CO). If water is electrolyzed at the same time, a mixture of hydrogen and CO is produced. This mixture, also called syngas, is the starting point of a large number of syntheses of hydrocarbons in the chemical industry. In this way, liquid transport fuels can be produced synthetically. If the electricity is generated by wind turbines or solar cells, then the use of the fuel is CO_2 neutral.

[0005] It is constantly an important issue to improve the efficiency and the lifetime of solid oxide cells. For example, US 2012/0003552 describes a method for improving the efficiency and durability of electrical energy storage using solid oxide electrolysis cells. More specifically, a set of reversible SOEC operating conditions is disclosed, whereby higher conversion efficiencies can be achieved. Further, US 2012/0251912 discloses a system design that incorporates an electrochemical device for energy storage. Said device can be a reversible SOEC that can operate in both discharge mode, i.e. power generation, and charge mode, i.e. electrolytic fuel production.

[0006] The SOEC system underlying the present invention comprises an SOEC stack, where the inlet gas on the fuel side as well as on the oxygen side must be pre-heated by means of a heating unit, so as to supply heat to the SOEC. This can for example be done using in-line electric heaters, e.g. with threads of Kanthal-type (Fe-Cr-Al alloy) in direct contact with the gas. The hot effluent gas from the SOEC stack is led to feed/effluent heat exchangers on the product side and the oxygen side, respectively.

[0007] In normal operation mode, oxygen is produced on the oxygen side and carbon monoxide is produced on the product side. This means that there are reducing conditions on the fuel side and oxidizing conditions on the oxygen side. During start-up, shut-down and trip, the

standard procedure would be to use an inert gas, i.e. nitrogen. This leads to the following issues:

[0008] If Kanthal-type threads are used in the fuel side and oxygen side heaters, then these threads become subject to nitridation and mechanical degradation when only nitrogen and non-oxidizing inert gases are present. This is because a kinetic competition exists between oxidation and nitridation. If oxygen or an oxidizing agent is present in the gas, then an oxide layer forming reaction is dominating. If, on the other hand, only nitrogen is present, then nitridation will occur.

[0009] The electrode on the oxygen side of the SOEC, e.g. Sr-doped $LaMnO_3$ (LSM), can be damaged or delaminate from the electrolyte, e.g. yttria-stabilised zirconia (YSZ), if there is no oxygen present on this side during start-up, shut-down and trip of the cell. During normal electrolysis operation oxygen is produced.

[0010] In order to mitigate the above issues and thereby enhancing the lifetime of the SOEC system, the present invention relates to a method for enhancing the lifetime of a solid oxide electrolysis cell system by counteracting nitridation of the threads of the in-line electrical heaters of the system, wherein start-up, shut-down and trip operations are done:

- in a humidified nitrogen atmosphere on the fuel side to achieve a dew point between -70°C and 23°C, and
- in air on the oxygen side or
- in carbon dioxide on the oxygen side,

and wherein sufficiently oxidizing conditions are always ensured across the whole surface of the cells on the oxygen side in the stack.

[0011] In the above method for enhancing the lifetime of a solid oxide electrolysis cell system by counteracting nitridation of the threads of the in-line electrical heaters of the system and the oxygen side of the cells, the normal operation is done with an oxidizing atmosphere on the oxygen side, said atmosphere consisting of carbon dioxide, air or mixtures thereof.

[0012] Regarding nitridation of the threads in the heater on the fuel side of the SOEC system, start-up, shut-down and trip can be conducted in the presence of nitrogen, but it has turned out that the nitrogen should be humidified to achieve a dew point above -70°C and below 23°C. This can for example be done by bubbling a side-stream of the nitrogen flow through water. This humidified nitrogen accomplishes a slightly oxidizing atmosphere which is sufficient to avoid any nitridation of the threads of the in-line electrical heaters.

[0013] In this case, adding water instead of another oxidant, such as CO_2 , has the benefit that if a voltage is applied to the SOEC with this feed gas, then no poisonous gas will be produced. This is not so if CO_2 is used, because then poisonous CO will be produced, which is not desirable in shut-down and trip situations.

[0014] For hydrogen, the critical safety issue is to avoid concentrations above 3% where explosions can occur in

air. This corresponds to avoiding dew points above 23°C. With a dew point of e.g. -50°C, the resulting hydrogen concentration will be only 0.005%.

[0015] Operation with low power consumption is critical for some applications, such as hot stand-by and battery-based shut-down in case of power failure. In this situation it is essential to operate with a split flow that can be adjusted so that the overall dew point for the gas entering the heater on the fuel side is -70°C or above.

[0016] As regards nitridation of the threads in the heater on the oxygen side, start-up and shut-down can be conducted in the presence of air. Regarding the oxygen side of the SOEC, start-up, shut-down and trip can also be conducted in the presence of air. During normal operation it may be necessary to operate with a recycle on the oxygen side to ensure that there are always sufficiently oxidizing conditions present across the total surface of the cells in the stack.

5. The method according to any of the claims 1-4, wherein the humidified nitrogen atmosphere is achieved by bubbling a side-stream of the nitrogen flow through water.

Claims

1. A method for enhancing the lifetime of a solid oxide electrolysis cell system by counteracting nitridation of the threads of the in-line electrical heaters of the system, wherein start-up, shut-down and trip operations are done:
 - in a humidified nitrogen atmosphere on the fuel side to achieve a dew point between -70°C and 23°C, and
 - in air on the oxygen side or
 - in carbon dioxide on the oxygen side,
 and wherein sufficiently oxidizing conditions are always present across the whole surface of the cells on the oxygen side in the stack.
2. A method according to claim 1 for enhancing the lifetime of a solid oxide electrolysis cell system by counteracting nitridation of the threads of the in-line electrical heaters of the system and the oxygen side of the cells, wherein normal operation is done with an oxidizing atmosphere on the oxygen side, said atmosphere consisting of carbon dioxide, air or mixtures thereof.
3. The method according to claim 1 or 2, wherein the system is operated with a recycle on the oxygen side to ensure that sufficiently oxidizing conditions are always present across the whole surface of the cells in the stack.
4. The method according to any of the claims 1-3, wherein the system comprises a split flow, which during operation can be adjusted, so that the overall dew point of the gas entering the heater on the fuel side is -70°C or above.



EUROPEAN SEARCH REPORT

Application Number
EP 14 16 4564

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 2005/233187 A1 (PASTULA MICHAEL [CA] ET AL) 20 October 2005 (2005-10-20) * claims 1,5 * * paragraph [0038] * -----	1-5	INV. C25B15/00 ADD. H01M8/04 H01M8/12
X	US 2006/222929 A1 (HICKEY DARREN [US] ET AL) 5 October 2006 (2006-10-05) * claims 1,11,13,14 * * table 1 * * paragraphs [0009], [0010], [0012] * -----	1-5	
Y	US 4 334 938 A (SHAY ROBERT H ET AL) 15 June 1982 (1982-06-15) * example 2 * * table II * * column 2, lines 18-28 * * column 4, lines 33-63 * -----	1-5	
Y	GB 1 259 847 A (ARMCO STEEL CORP [US]) 12 January 1972 (1972-01-12) * claims 1,4,5 * * page 2, lines 18-91 * -----	1-5	TECHNICAL FIELDS SEARCHED (IPC)
Y	EP 0 745 446 A1 (AIR PROD & CHEM [US]) 4 December 1996 (1996-12-04) * claims 1,2 * * column 6, line 32 - column 7, line 10 * * column 7, lines 24-29 * * column 8, lines 4-13,41-51 * * column 10, lines 9-32 * -----	1-5	C25B H01M
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 30 September 2014	Examiner Perednis, Dainius
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1
EPO FORM 1503 03.02 (P/M/C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 14 16 4564

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-09-2014

10

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
US 2005233187	A1	20-10-2005	AU 2005234097 A1	27-10-2005
			CA 2562716 A1	27-10-2005
			EP 1743395 A1	17-01-2007
			JP 5276318 B2	28-08-2013
			JP 2007533084 A	15-11-2007
			US 2005233187 A1	20-10-2005
			US 2011111310 A1	12-05-2011
			WO 2005101556 A1	27-10-2005

US 2006222929	A1	05-10-2006	NONE	

US 4334938	A	15-06-1982	BR 8105325 A	04-05-1982
			CA 1176546 A1	23-10-1984
			DE 3174564 D1	12-06-1986
			EP 0046567 A2	03-03-1982
			JP H0118966 B2	10-04-1989
			JP S57114609 A	16-07-1982
			US 4334938 A	15-06-1982
			ZA 8105663 A	25-08-1982

GB 1259847	A	12-01-1972	BE 731483 A	15-09-1969
			CA 933072 A1	04-09-1973
			DE 1919208 A1	30-10-1969
			ES 366233 A1	16-03-1971
			FR 2006577 A1	26-12-1969
			GB 1259847 A	12-01-1972
			NL 6906067 A	21-10-1969

EP 0745446	A1	04-12-1996	CA 2177428 A1	02-12-1996
			DE 69608026 D1	08-06-2000
			DE 69608026 T2	21-12-2000
			EP 0745446 A1	04-12-1996
			US 5613185 A	18-03-1997

15

20

25

30

35

40

45

50

55

EPC FORM P0469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20120003552 A [0005]
- US 20120251912 A [0005]