



In operando studies of ScYSZ electrolyte supported symmetric solid oxide cell by X-ray Diffraction at ESRF, ID06 Beamline

Sierra, J. X.; Poulsen, H. F.; Jørgensen, P. S.; Detlefs, C.; Cook, P.; Simons, H.; Yildirim, C.; Ahl, S. R.; Jakobsen, A. C.; Kantor, I.

Publication date:
2017

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Sierra, J. X., Poulsen, H. F., Jørgensen, P. S., Detlefs, C., Cook, P., Simons, H., ... Bowen, J. R. (2017). *In operando studies of ScYSZ electrolyte supported symmetric solid oxide cell by X-ray Diffraction at ESRF, ID06 Beamline*. Poster session presented at 3rd International Conference on Tomography of 3D Materials and Structures, Lund, Sweden.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.


In operando studies of ScYSZ electrolyte supported symmetric solid oxide cell by X-ray Diffraction at ESRF, ID06 Beamline

J.X. Sierra¹, H. F. Poulsen², P. S. Jørgensen¹, C. Detlefs³, P. Cook³, H. Simons², C. Yildirim³, S. R. Ahl², A. C. Jakobsen², I. Kantor², J. R. Bowen¹
 1: Technical University of Denmark (DTU Risø), 2: Technical University of Denmark (DTU Lyngby), 3: ESRF Beamline ID06
 jxst@dtu.dk





Introduction

Solid Oxide Cells are becoming a promising solution for sustainable and renewable power generation. Scandium doped Ytria Stabilized Zirconia is considered one of the best materials used as electrolyte because of its high ionic conductivity and great mechanical and chemical stability under operating conditions. Oxygen bubble formation at grain boundaries of ScYSZ near the anode/electrolyte interface has been observed as a degradation process when running in electrolysis mode at 800 - 900 °C for 24 - 72 hours at high current densities. X-ray diffraction can provide information about structural evolution at different depths of the cell during operation.




Structural evolution and oxygen bubble formation


Setup of the synchrotron beamline hutch at ESRF - ID06 Beamline:




Estimated stress across the cell only from Δd -spacing



Relative d-spacing of (111) diffraction line across the cell and schematic view of the cell polarization and bubbles found.




Oxygen bubble formation in electrolyte close to the anode region




Dark Field X-Ray Diffraction Microscopy

At ID06 beamline we are currently commissioning a dark field microscope, which enables zooming in on mm-sized samples and perform 3D mapping of grains and stresses at a 100 nm scale in regions of 200 μm . This provides unprecedented opportunities for studying microstructural changes in operando materials.




An objective lens composed of several beryllium lenses magnifies the projection of a diffracting grain.

Strain map



In another experiment run at 900 °C, snapshots at 0V and 2V were taken with an interval of few seconds. The internal processes of the electrolyte grains are unknown, further investigations are expected to provide more information.



Results

A gradient in d-spacing is observed across the cell after 24 hours, which can be a contribution from the oxygen bubble formation and a phase change from the zirconia reduction. X-ray microscopy revealed changes in the morphology and strain domains inside one grain after 10 hours running at operating conditions. Snapshots show changes in the internal structure when the current is applied.

References

- H. Simons, et al., Nature Communications. DOI: 10.1038/ncomms7098. 2015
- R. Knibbe, et al., Journal of The Electrochemical Society, 157 (8) B1209-B1217 2010
- F. Tietz, et al., Journal of Power Sources, 223 (2013) 129-135
- A. Hagen, et al., Journal of Synchrotron Radiation (2012). 19, 400-407. DOI: 10.1107/S0909049512006760

Acknowledgements

This project is in collaboration with the ESRF Beamline ID06.

We thank the ERC Advanced Grant